



Renewable Lubricants, Inc.
476 Griggy Rd. NE, PO Box 474
Hartville, OH 44632-0474
Voice: 330.877.9982 Fax: 330.877.2266
www.renewablelube.com

Bio-AW/AL™ Hydraulic Press Oils **ISO 32, 46, 68**

STABILIZED™
by Renewable Lubricants

"Biobased Lubricants that Perform Like Synthetics"

Bio-AW/AL™ Hydraulic Press Oils are ultimately biodegradable¹ vegetable based formulas that replace mineral oil based hydraulic fluids in demanding press hydraulic systems. Bio-AW/AL™ Hydraulic Press Oils are formulated to perform in hydraulic systems that require Anti-Wear (AW), Anti-Leak (AL), anti-rust, anti-oxidation, anti-foam, and demulsibility properties. Bio-AW/AL™ Hydraulic Press Oils contain the same performance benefits and additive technology as the Bio-Ultimax™ 1000 Hydraulic Fluids with the addition of the anti-leak and/or non-drip performance. They are highly inhibited against moisture and rusting in both fresh and sea water and pass both A and B Sequences of the ASTM D-665 Turbine Oil Rust Test. Incorporating the super high viscosity index of the Stabilized* High Oleic Base Stocks (HOBS) into the formula, increases the viscosity index past synthetic levels (Energy Conserving Formulas). A zinc-free (ashless) additive system has also been developed that is environmentally friendly and meets or exceeds pump requirements.

Bio-AW/AL™ Hydraulic Press Oils are designed for use in mobile and stationary hydraulic vane, piston, and gear-type pumps when used in accordance with the equipment manufacturer. **Very little wear was encountered, 0 to 25mg (Pass), in accelerated biobased tests using Denison T-5D, Vickers 20VQ, 35VQ-25 (M-2950-S), and V-104C (ASTM D-2882) pump stand tests at pressures and temperatures ranging from 2000 to 3000 psi and from 150⁰ to 210⁰ F.** The anti-wear performance exceeds the load stage 10 in the FZG (DIN 51354) requirements for US Steel 136, DIN 51524, and GM (LS-2). They also meet the requirements for ashless GL-3 gear oils in reduction units and gear sets where they meet the viscosity ranges.

The super high viscosity index of the HOBS naturally improves the thermal shear stability of the formula and increases load capacity. The HOBS's extremely low volatility increases the flash and fire safety features in the formula. They are formulated to provide seal conditioning for longer seal life and to reduce oil leakage from the system. Bio-AW/AL™ Hydraulic Press Oils should be used in hydraulic systems where low toxicity, and BIODEGRADABILITY properties are required. Base oils and additives in these products pass and exceed the acute toxicity (LC-50) criteria adopted by the US Fish and Wildlife Service and the US EPA. Bio-AW/AL™ Hydraulic Press Oils are ENVIRONMENTALLY RESPONSIBLE lubricants that are formulated from renewable agricultural plant resources. We believe Earth's environmental future rests in the use of renewable materials.

STABILIZED by Renewable Lubricants* is RLI's trademark on their proprietary and patented anti-oxidant, anti-wear, and cold flow technology. High Oleic Base Stock (HOBS) are agricultural vegetable oils. This Stabilized technology allows the HOBS to perform as a high performance formula in high and low temperature applications, reducing oil thickening and deposits.

¹ Ultimate Biodegradation (Pw1) within 28 days in ASTM D-5864 Aerobic Aquatic Biodegradation of Lubricants

Patented Product: US Patent 6,383,992, US Patent 6,534,454 with additional Pending and Foreign Patents

* Trademark of Renewable Lubricants, Inc.

Copyright 1999 Renewable Lubricants, Inc.

Availability F.O.B. :Hartville, Ohio, USA 5 Gallon Pails Drums Bulk

Bio-AW/AL™ Hydraulic Press Oils ISO 32, 46, 68

The test data below show that the Bio-AW/AL™ Hydraulic Press Oils provide high performance in a wide variety of stationary and transportation equipment that operate in broad ranges of environmental conditions. In equipment operating outside, wear from poor cold temperature pumpability, surge loads, moisture, and dusty environments are more prominent. Bio-AW/AL™ Hydraulic Press Oils are formulated to improve performance in equipment that requires excellent anti-wear, anti-leak, hydrolytic stability, and cold temperature pumpability as low as -35°C.

TYPICAL SPECIFICATIONS	METHOD	ISO 32	ISO 46	ISO 68	Spec. Requirements
Specific Gravity @ 15.6°C	ASTM D-287	0.874	0.876	0.886	Report
API Gravity @ 15.6°C	ASTM D-287	30.4	30.0	28.2	Report
Viscosity @ 40°C	ASTM D-445	30.87	43.8	64.1	Note 1
Viscosity @ 100°C	ASTM D-445	6.9	9.67	12.5	Note 1
Viscosity @ -15°C, Brookfield	ASTM D-2983	not complete	1100 cP	----	Note 1
Viscosity @ -25°C, Brookfield	ASTM D-2983	1,200 cP	3,000 cP	----	Note 1
Viscosity @ -30°C MRV TP1	ASTM D-4684	4,500 cP	8,000 cP	----	10W= <60,000
Viscosity @ -35°C MRV TP1	ASTM D-4684	7,500 cP	----	----	5W= <60,000
Viscosity Index	ASTM D-2270	184	216	198	90 (min)
Pour Point	ASTM D-97	-40°C	-36°C	-30°C	Note 1
Flash Point (COC)	ASTM D-92	236°C	243°C	251°C	198°C (min)
Fire Point (COC)	ASTM D-92	260°C	268°C	274°C	218°C (min)
Hydrolytic Stability, Copper Wt. Loss (mg) Copper Appearance Water Layer	ASTM D-2619	0.0139 1B <4	0.0208 1B <4	0.0208 1B <4	0.2 Report 4
Foam Sequence I, II, III (10 min)	ASTM D-892	0 Foam	0 Foam	0 Foam	0 Foam
Rust Prevention Distilled Water Syn. Sea Water	ASTM D-665	Pass Pass	Pass Pass	Pass Pass	Pass Pass
Copper Corrosion Strip 3hr @ 100°C	ASTM D-130	1B	1B	1B	DIN 51524 2(max)
Rotary Bomb Oxidation, (minutes)	ASTM D-2272	360	360	360	USS 120 (min)
Oxidation Stability (Pressure Differential Scanning Calorimeter) min	ASTM D-5483 Modified	70.0 (165°C)	70.0 (165°C)	70.0 (165°C)	Note 2
Neutralization Number mg KOH/g	ASTM D-974	<0.4	<0.4	<0.4	1.5 (max)
Swell of Synthetic NBR-L Rubber, % (Avg.) Volume Change (%) Shore A Hardness Change (%)	DIN 53538, Part 1	6.0 -4	6.0 -4	6.0 -4	0 to 12 0 to -7
Filterability A-No Water (s) (Avg) B-2% Water (s) (Avg)	Denison TP 02100 HF-0 Requirement	113 187	268 271	335 449	600 (max) 2xA (max)
Demulsibility, ML Oil/Water/Emulsion	ASTM D-1401	40/ 40/ 0	40/ 40/ 0	40/40/0	40/37/3 (max)
4-Ball Wear, 1h, 167°F, 1200 RPM, 40 kg	ASTM D-4172	0.3 – 0.4	0.3 – 0.4	0.3 – 0.4	USS 127 0.5 (max)
FZG Test	DIN 51354	12	12	12	US.Steel 10 (min)
<u>Biodegradation Classification</u>	ASTM D-5864	Ultimate PW1	Ultimate PW1	Ultimate PW1	Ultimate PW1
<i>Note 1 Viscosity Sufficient for Application</i>					
<i>Note 2 Not Required</i>					